

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 719 743 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
17.03.1999 Bulletin 1999/11

(51) Int. Cl.<sup>6</sup>: **C03C 17/30**, C03C 17/00,  
C09K 3/18

(21) Application number: 95119467.9

(22) Date of filing: 11.12.1995

**(54) Water repellent surface treatment with integrated primer**

Wasserabweisende Oberflächenbehandlung mit integriertem Grundiermittel

Traitement de surface hydrofuge avec un revêtement primaire intégré

(84) Designated Contracting States:  
AT BE CH DE DK ES FR GB GR IT LI LU NL SE

(30) Priority: 27.12.1994 US 363803

(43) Date of publication of application:  
03.07.1996 Bulletin 1996/27

(73) Proprietor: PPG INDUSTRIES, INC.  
Pittsburgh Pennsylvania 15272 (US)

(72) Inventor: Goodwin, George B.  
Cranberry Township, Pa. 16066 (US)

(74) Representative:  
Fleischer, Holm Herbert, Dr. et al  
Patentanwälte Sternagel & Fleischer  
Braunsberger Feld 29  
51429 Bergisch Gladbach (DE)

(56) References cited:  
EP-A- 0 513 727 EP-A- 0 545 201  
EP-A- 0 548 775 DE-A- 4 218 657

Remarks:

The file contains technical information submitted  
after the application was filed and not included in  
this specification

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 0 719 743 B1**

## Description

CROSS REFERENCE TO RELATED APPLICATION

- 5 [0001] This application is a continuation-in-part of U.S. Application Serial No. 08/220,353 filed March 30, 1994, which is a continuation-in-part of U.S. Application Serial No. 07/589,235 filed September 28, 1990, now U.S. Patent No. 5,308,705, which is a continuation-in-part of Application Serial No. 07/503,587 filed April 3, 1990, which is now U.S. Patent No. 4,983,459.

10 BACKGROUND

[0002] The present invention relates generally to the art of surface treatment and, more particularly, to the art of producing a water repellent surface on various substrates, and most particularly to improving the durability of such water repellent surfaces.

15 THE PRIOR ART

[0003] European Patent Application No. 92107814.3 (Publication Number 0 513 690 A2) of Yoneda et al. describes a surface-treated substrate having at least two treated surface layers wherein the first outermost layer is obtained by treatment with a compound forming a surface having a contact angle of at least 70° against water and the second underlayer is obtained by treatment with at least one reactive silane compound selected from isocyanate silane compounds and hydrolyzable silane compounds.

[0004] U.S. Patent Nos. 4,983,459 and 4,997,684 to Franz et al. disclose an article and method respectively for providing a durable nonwetting surface on glass by treatment with a perfluoroalkylalkyl silane and a fluorinated olefin telomer.

[0005] In U.S. Patent No. 5,308,705 Franz et al. describe providing nonwetting surface properties to substrates other than glass by treatment with a perfluoroalkylalkyl silane and a fluorinated olefin telomer.

[0006] In U.S. Patent No. 5,328,768 Goodwin discloses a glass substrate the surface of which is treated with first a silica primer layer and second a perfluoroalkylalkyl silane.

20 [0007] EP-A-548 775 relates to a metal oxide film formed on a glass substrate by the so-gel process. To afford water repellency to the oxide film a fluoroalkylsilane is mixed with an alkoxysilane solution, diluted with a solvent and then water is added in the amount of 100 mol% to 1000 mol% of the total amounts of the fluoroalkylsilane and the alkoxysilane so as to partially hydrolyze the fluoroalkylsilane and the alkoxysilane, thereby forming a sol.

[0008] In EP-A-513 727 a water repellent glass is disclosed whereby a water repellent film is coated on the substrate by applying a solution comprising a first silicone alkoxide, a second silicone alkoxide whereby part of the alkoxyl groups are substituted with a fluoroalkyl group, alcohol, water, and a catalyst like acid or base, to promote hydrolysis and polycondensation of these compounds.

25 [0009] DE-A-42 18 657 refers to the preparation of a water repellent metal oxide film on a glass substrate by mixing a first solution of a metal oxide precursor selected from the groups consisting of metal alkoxides and metal acetylacetonates with an organic solvent and water in an amount of 50 to 400 mol% of the metal oxide precursor thereby preparing a first sol by hydrolysis and polycondensation of the at least one metal oxide precursor. Thereafter a fluoroalkylsilane compound is added in a specific amount. The resultant sol is then applied to the glass substrate.

40 SUMMARY OF THE INVENTION

45 [0010] The present invention provides a substrate surface with high water repellency and high lubricity. The durability of the water and dirt repellency of a substrate surface is improved by applying to the substrate surface a composition comprising a mixture of a perfluoroalkylalkylsilane compound and a hydrolyzable silane compound, whereby no water is added to said mixture. The hydrolyzable silane compound is a compound capable of hydrolytic condensation to form silica gel and functions as an integral primer compound. The surface treatment of the present invention provides enhanced durability to the water and dirt repellent surface without requiring a separate primer layer. High water repellency and lubricity are provided by perfluoroalkylalkylsilane. The hydrolyzable silane also provides for reactive drying of the solvent. The perfluoroalkylalkylsilane and hydrolyzable silane surface treatment of the present invention also provides enhanced abrasion resistance to the substrate surface. Increased resistance to humidity, ultraviolet radiation and mechanical abrasion are provided by the silane compound capable of hydrolytic condensation to silica gel.

## DESCRIPTION OF THE PREFERRED EMBODIMENT

[0011] Durability of rain and soil repellency provided by application of a perfluoroalkylalkylsilane to a substrate surface is enhanced by mixing a silane or mixture of silanes capable of hydrolysis to silica gel with a perfluoroalkylalkylsilane prior to application. In accordance with the present invention, a mixture of a perfluoroalkylalkylsilane and silane or mixture of silanes capable of hydrolysis to silica gel is applied to the surface of glass to form a coating which is more durable than would have been formed without the silane or mixture of silanes capable of hydrolysis to silica gel.

[0012] Perfluoroalkylalkylsilane and hydrolyzable silane are applied to the surface of a substrate to produce the article of the present invention preferably as a colloidal suspension or solution, preferably in an aprotic solvent, preferably an alkane or mixture of alkanes, or a fluorinated solvent. The preferred solution of the present invention is applied to a substrate surface by any conventional technique such as dipping, flowing, wiping or spraying. The solvent is evaporated and the composition forms a durable, non-wetting, lubricating surface with improved abrasion resistance. The present invention provides the durability benefits of a primer without the additional step of applying a separate primer layer. The use of the completely hydrolyzable silane improves the humidity, ultraviolet light, and abrasion resistance of the silane surface treatment as measured by the Cleveland Condensing Cabinet, QUV (with FS40 or B313 lamps), and wet sled abrasion tests, indicating a longer useful product lifetime.

[0013] Preferred silanes capable of hydrolysis to silica gel have the general formula  $\text{SiX}_4$ , wherein X is a radical such as halogen, alkoxy, or acyl, preferably chloro, bromo, iodo, methoxy, ethoxy, and acetoxy. Preferred hydrolyzable silanes include tetrachlorosilane and tetraacetoxysilane.

[0014] The silanes,  $\text{SiX}_4$ , serve two functions. One is to become part of the coating and impart resistance to weathering and abrasion. Another function is to dry the solvent. Typical hydrocarbon solvents can contain 50 to 200 ppm of water. Other solvents can be much higher in water content. For example, a solvent containing 200 ppm water would have enough water present to deactivate a perfluoroalkylalkylsilane at 0.5 weight percent concentration. The completely hydrolyzable silane is capable of eliminating or reducing the water content of the solvent prior to perfluoroalkylalkylsilane addition. Otherwise, water deactivation of the perfluoroalkylalkylsilane would lead to insufficient coating deposition or very poor durability.

[0015] Preferred perfluoroalkylalkylsilanes have the general formula  $\text{R}_m\text{R}'_n\text{SiX}_{4-m-n}$ , wherein R is a perfluoroalkylalkyl radical; m is typically one, n is typically zero or one, and m+n is less than 4; R' is a vinyl or an alkyl radical, preferably methyl, ethyl, vinyl or propyl; and X is preferably a radical such as halogen, acyloxy, and/or alkoxy. Preferred perfluoroalkyl moieties in the perfluoroalkylalkyl radicals range from  $\text{CF}_3$  to  $\text{C}_{30}\text{F}_{61}$ , preferably  $\text{C}_6\text{F}_{13}$  to  $\text{C}_{18}\text{F}_{37}$ , and most preferably  $\text{C}_8\text{F}_{17}$  to  $\text{C}_{12}\text{F}_{25}$ ; the alkyl moiety is preferably ethyl. R' is preferably methyl or ethyl. Preferred radicals for X include hydrolyzable chloro, bromo, iodo, methoxy, ethoxy and acetoxy radicals. Preferred perfluoroalkylalkylsilanes in accordance with the present invention include perfluoroalkylethyltrichlorosilane, perfluoroalkylethyltrimethoxysilane, perfluoroalkylethyltriacetoxysilane, perfluoroalkylethylidichloro(methyl)silane and perfluoroalkylethylidethoxy(methyl)silane.

[0016] These preferred perfluoroalkylethylsilanes appear to react with bonding sites at the substrate surface on a molecular basis. Strong surface bonding of the perfluoroalkylethylsilanes produces a durable substrate surface which exhibits a high contact angle with a drop of water, indicating high water repellency.

[0017] Suitable solvents include isopropanol, ethanol, hexane, heptane, mineral spirits, acetone, toluene and naphtha. Preferred solvents are alkanes or halogenated hydrocarbon solvents such as trichlorotrifluoroethane, and methylene chloride, and perfluorinated organic compounds such as perfluorocarbons. Concentrations of about 0.005 to 50, preferably about 0.05 to 5, percent of silane are preferred. The solvent is preferably evaporated simply by drying in air at ambient temperature, or may be removed by wiping. The silanes may also be crosslinked to form a more durable coating. Preferably, curing is accomplished by heating the silane treated surface. Typically, curing temperatures of at least 150°F (about 66°C) are preferred, particularly above 200°F (about 93°C). A cure cycle of about 200°F (about 93°C) for about 30 minutes is suitable. Higher temperatures and shorter heating times may be more efficient. A cure cycle of 2 to 5 minutes at 400 to 500°F (about 204 to 260°C) may be preferred, particularly about 3 minutes at about 470°F (about 243°C). The substrate surfaces may, in the alternative, be contacted with perfluoroalkylalkylsilane in vapor form.

[0018] The contact angles recited herein are measured by the sessile drop method using a modified captive bubble indicator manufactured by Lord Manufacturing, Inc., equipped with Gaertner Scientific goniometer optics. The surface to be measured is placed in a horizontal position, facing upward, in front of a light source. A drop of water is placed on top of the surface in front of the light source so that the profile of the sessile drop can be viewed and the contact angle measured through the goniometer telescope equipped with circular protractor graduation.

[0019] Weathering chambers include the Cleveland Condensing Cabinet (CCC) and QUV Tester (products of The Q-Panel Company, Cleveland, OH). The CCC chamber was operated at a vapor temperature of 140°F (60°C) in an indoor ambient environment which resulted in constant water condensation on the test surface. The QUV Tester is operated with cycles of 8 hours UV (either B313 or FS40 lamps) at black panel temperature of 65-70°C and 4 hours condensing

humidity at 50°C.

[0020] The present invention will be further understood from the descriptions of specific examples which follow.

#### EXAMPLE I

[0021] A solution was prepared by mixing one gram of tetrachlorosilane and one gram of perfluoroalkylalkylsilane in 40 grams of trichlorotrifluoroethane (Freon® TF solvent, a product of DuPont). The perfluoroalkylalkylsilane comprised perfluoroalkylethyltrichlorosilanes, wherein the perfluoroalkyl moieties comprised primarily C<sub>6</sub>F<sub>13</sub> to C<sub>18</sub>F<sub>37</sub>. For comparison, a control solution was mixed without the tetrachlorosilane. The solutions were applied to the atmosphere surface of 3.9 millimeter thick Solex® float glass (product of PPG Industries, Inc.) with a cotton pad. Coupons were cured at 200°F (93°C) for one hour. The excess silane was removed from the glass surfaces by solvent washing. Coupons were weathered in the CCC and QUV-FS40 weathering cabinets. Coating efficiency was measured by the contact angle of a sessile drop of water. The results are shown in the following table.

Table I

CCC			QUV-FS40		
Hours	Primer	No Primer	Hours	Primer	No Primer
0	105°	105°	0	107°	106°
496	102°	87°	319	106°	102°
927	67°	60°	1332	91°	89°
1669	49°	40°	2115	83°	79°
			2498	78°	70°
			2943	72°	57°

#### EXAMPLE II

[0022] Four solutions were prepared, each of which was 0.5 percent by weight perfluoroheptyltriethoxytrichlorosilane in Isopar L solvent (product of Exxon), a mixture of alkanes. The solutions had tetrachlorosilane concentrations of 0.0, 0.2, 0.45, and 0.79 percent by weight. The order of addition was Isopar L, tetrachlorosilane and perfluoroalkylethyltrichlorosilane to utilize the reactive drying of the solvent by the hydrolyzable tetrachlorosilane. These four solutions were coated on the tin surface of coupons of 0.182 inch (4.6 millimeter) thick clear float glass. Samples were tested in the CCC chamber. Coating efficiency was measured by the contact angle of a sessile drop of water. It can be seen in the following table that increasing the concentration of hydrolyzable silane within this range improves the durability of the perfluoroalkylalkylsilane surface treatment.

Table II

Hours	CCC Contact Angle (°)			
	Primer Concentration (Percent by Weight)			
	0	0.2	0.45	0.79
0	115	115	114	114
122	81	89	105	105
284	54	65	77	81
475	36	44	58	69
642	--	--	--	47

# EP 0 719 743 B1

## EXAMPLE III

[0023] Four solutions were prepared, each of which was 2.5 percent by weight of the perfluoroalkylethyltrichlorosilane described in Example I and 2.5 percent by weight perfluoroalkylethylene in Fluorinert® FC-77 solvent (a product of 3M). The solutions had tetrachlorosilane concentrations of 0.0, 1.0, 2.0 and 5.0 percent by weight. These four solutions were coated on the tin surface of coupons of 0.187 inch (4.7 millimeter) thick clear float glass. Coupons were cured at 300°F (149°C) for 15 minutes. Samples were tested in the CCC and QUVB-313 chambers. Coating efficiency was measured by contact angle of a sessile drop of water. Results are given in the following tables.

Table IIIA

Hours	CCC Contact Angle (°)			
	Primer Concentration (Percent by Weight)			
	0	1.0	2.0	5.0
0	113	113	115	114
162	95	109	114	112
348	73	81	98	93
684	31	41	43	34

Table IIIB

Hours	QUVB-313 Contact Angle (°)			
	Primer Concentration (Percent by Weight)			
	0	1.0	2.0	5.0
0	113	114	117	116
566	107	111	111	109
1375	82	95	95	87
2095	72	80	84	71

## EXAMPLE IV

[0024] Solutions were prepared comprising 0.5 percent by weight perfluoroalkylethyltrichlorosilane with and without 0.5 percent by weight tetrachlorosilane in Isopar® L solvent. Three perfluoroalkylethyltrichlorosilanes were employed: 1H,1H,2H,2H-tridecafluorooctyltrichlorosilane ("octyl"), 1H,1H,2H,2H-heptadecafluorodecyltrichlorosilane ("decyl"), or a mixture of perfluoroalkylethyltrichlorosilanes described in Example I. Tempered Solex® glass coupons and clear float glass coupons that had undergone a heat treatment which simulates a bending cycle (without bending significantly) were used in this study. The Solex glass was 0.157 inch (4 millimeters) thick, the clear float was 0.090 inch (2.3 millimeters) thick, and the tin surfaces were treated. Samples were tested in the QUVB-313 chamber and on a Wet Sled Abrader (Sheen Instruments LTD, Model 903). The Wet Sled Abrader was custom modified with an aluminum block which held two automotive windshield wiper blades. The wet sled abrasion test thus configured has an unusually high pressure wiper arm loading and is done partially wet and partially dry. These wiper strokes are much more severe than normally used in vehicles. Coating efficiency was measured by the contact angle of a sessile drop of water. The plus sign "+" refers to the presence of tetrachlorosilane in the coating formulations in the following tables.

Table IVA

Hours	QUVB-313 Contact Angle (°)					
	octyl	octyl+	decyl	decyl+	mix	mix+
0	116	112	111	115	111	118
163	102	105	87	112	102	116
352	95	95	84	107	100	111
496	82	88	74	102	89	106
659	79	80	66	93	82	99
827	70	85	60	89	82	103

Table IVB

Cycles	Wet Sled Abrasion Contact Angle (°)					
	octyl	octyl+	decyl	decyl+	mix	mix+
0	113	117	111	116	115	117
200*	86	104	79	108	86	108
600*	52	99	78	106	79	105
5000	35	84	47	91	82	92

\*These data (at 200 and 600 cycles) were obtained with a slurry of 0.5 percent by weight Hi-Sil® 233 synthetic precipitated silica in water. The data for 5000 cycles were obtained using deionized water only.

### EXAMPLE V

[0025] A control solution was prepared by mixing 95 grams of FC-77 solvent, 2.5 grams of perfluoroalkylethyltrichlorosilanes (perfluoroalkyl =  $C_6F_{13}$  to  $C_{18}F_{37}$ ), and 2.5 grams of perfluoroalkylethylene. A primer-containing solution was prepared by mixing 188 grams of FC-77 solvent, 5 grams of perfluoroalkylethyltrichlorosilanes, 5.0 grams of perfluoroalkylethylene (perfluoroalkyl =  $C_6F_{13}$  to  $C_{18}F_{37}$ ), and 2 grams of tetrachlorosilane. A primer only solution was prepared from 198.4 grams of FC-77 solvent and 1.6 grams of tetrachlorosilane. These solutions were applied to the tin surface of 4.9 millimeter thick clear float glass with a cotton pad. Selected coupons were coated with primer solution prior to coating with either control solution or the solution containing perfluoroalkylalkylsilane and tetrachlorosilane. Coupons were cured at 300°F (149°C) for 15 minutes. The excess silane was removed from the glass surfaces by solvent washing. Coupons were weathered in the CCC. Coating efficiency was measured by the contact angle of a sessile drop of water.

Table V

Hours	CCC Contact Angle (°)			
	No primer layer		Primer layer	
	No integral primer	Integral primer	No integral primer	Integral primer
0	114	114	113	114
232	116	116	117	115
398	100	110	109	110

Table V (continued)

Hours	CCC Contact Angle (°)			
	No primer layer		Primer layer	
	No integral primer	Integral primer	No integral primer	Integral primer
590	49	78	75	86
918	29	39	31	41

The solution containing a silane hydrolyzable to silica led to more durable coatings whether or not the glass was preprimed with a silica layer separately with a solution of a hydrolyzable silane.

[0026] The above examples are offered to illustrate the present invention. Various perfluoroalkylalkylsilanes, hydrolyzable silanes, solvents and concentrations may be applied by any conventional technique, and optimally cured at suitable temperatures for adequate times to provide durable non-wetting surfaces to any of a variety of glass and plastic substrates, as well as other inorganic surfaces such as metals, ceramics, enamels, and metal or metal oxide films. The treated substrates of the present invention are especially suitable in automobile and aircraft parts, as well as in building components.

## Claims

1. An article comprising a substrate at least a portion of the surface of which is treated with a composition comprising a mixture of perfluoroalkylalkylsilane and completely hydrolyzable silane wherein the substrate is selected from the group consisting of glass, plastics, metals, organic polymer coated substrates and inorganic coated substrates, whereby no water is added to said mixture.
2. An article according to claim 1, wherein said perfluoroalkylalkylsilane is selected from compounds having the general formula  $R_m R'_n SiX_{4-m-n}$ , wherein R is a perfluoroalkylalkyl radical, R' is a vinyl or an alkyl radical, m+n is less than 4, and X is selected from the group consisting of halogen, alkoxy and acyl radicals.
3. An article according to claim 2, wherein the perfluoroalkyl moiety of said perfluoroalkylalkyl radical is selected from the group consisting of  $CF_3$  to  $C_{30}F_{61}$ .
4. An article according to claim 3, wherein said perfluoroalkyl moiety is selected from the group consisting of  $C_6F_{13}$  to  $C_{18}F_{37}$ .
5. An article according to claim 4, wherein said perfluoroalkyl moiety is selected from the group consisting of  $C_8F_{17}$  to  $C_{12}F_{25}$ .
6. An article according to claim 2, wherein R' is selected from the group consisting of methyl, ethyl, vinyl and propyl.
7. An article according to claim 3, wherein X is selected from the group consisting of chloro, bromo, iodo, methoxy, ethoxy and acetoxy.
8. An article according to claim 2, wherein said perfluoroalkylalkylsilane is selected from the group consisting of perfluoroalkylethyltrichlorosilane, perfluoroalkylethyltrimethoxysilane, perfluoroalkylethyltriethoxysilane, perfluoroalkylethyltriacetoxysilane, perfluoroalkylethyltrichlorosilane and perfluoroalkylethyltriethoxy(methyl)silane.
9. An article according to claim 8, wherein said composition further comprises a fluorinated olefin.
10. An article according to claim 1, wherein said completely hydrolyzable silane is selected from the group consisting of silanes having the general formula  $SiX_4$ , wherein X is selected from the group consisting of halogen, alkoxy and acyl radicals.
11. A method of producing a non-wetting surface on a substrate comprising contacting a surface with a composition comprising a mixture of perfluoroalkylalkylsilane and completely hydrolyzable silane wherein said substrate is selected from the group consisting of glass, plastics, metals, organic polymer coated substrates and inorganic coated substrates, whereby no water is added to said mixture.

12. A method according to claim 11, wherein said perfluoroalkylalkylsilane is selected from compounds having the general formula  $R_mR'_nSiX_{4-m-n}$  wherein R is a perfluoroalkylalkyl radical, R' is a vinyl or an alkyl radical, m+n is less than 4, and X is a radical selected from the group consisting of halogen, alkoxy and acyl radicals.
13. A method according to claim 12, wherein the perfluoroalkyl moiety of said perfluoroalkylalkyl radical is selected from the group consisting of  $CF_3$  to  $C_{30}F_{61}$ .
14. A method according to claim 13, wherein said perfluoroalkyl moiety is selected from the group consisting of  $C_6F_{13}$  to  $C_{18}F_{37}$ .
15. A method according to claim 14, wherein said perfluoroalkyl moiety is selected from the group consisting of  $C_8F_{17}$  to  $C_{12}F_{25}$ .
16. A method according to claim 12, wherein R' is selected from the group consisting of methyl, ethyl, vinyl and propyl.
17. A method according to claim 12, wherein X is selected from the group consisting of chloro, bromo, iodo, methoxy, ethoxy and acetoxy.
18. A method according to claim 11, wherein said composition further comprises a fluorinated olefin.
19. A method according to claim 11, wherein the hydrolyzable silane is selected from the group consisting of silanes having the general formula  $SiX_4$ , wherein X is selected from the group consisting of halogen, alkoxy and acyl radicals.
20. A method according to claim 11, wherein the substrate surface is first primed with a layer of silica.

#### Patentansprüche

1. Gegenstand enthaltend ein Substrat, dessen Oberfläche wenigstens teilweise mit einer Zusammensetzung behandelt ist, die eine Mischung aus Perfluoralkylalkylsilan und vollständig hydrolysierbarem Silan enthält, wobei das Substrat ausgewählt ist aus der Gruppe bestehend aus Glas, Kunststoffen, Metallen, mit einem organischen Polymer beschichteten Substraten und anorganisch beschichteten Substraten, wobei dieser Mischung kein Wasser zugesetzt ist.
2. Gegenstand nach Anspruch 1, wobei dieses Perfluoralkylalkylsilan ausgewählt ist aus Verbindungen mit der allgemeinen Formel  $R_mR'_nSiX_{4-m-n}$ , worin R ein Perfluoralkylalkylrest ist, R' ein Vinyl- oder ein Alkylrest ist, m+n kleiner als 4 ist und X ausgewählt ist aus der Gruppe bestehend aus Halogen-, Alkoxy- und Acylresten.
3. Gegenstand nach Anspruch 2, wobei die Perfluoralkyleinheit dieses Perfluoralkylalkylrestes ausgewählt ist aus der Gruppe bestehend aus  $CF_3$  bis  $C_{30}F_{61}$ .
4. Gegenstand nach Anspruch 3, wobei diese Perfluoralkyleinheit ausgewählt ist aus der Gruppe bestehend aus  $C_6F_{13}$  bis  $C_{18}F_{37}$ .
5. Gegenstand nach Anspruch 4, wobei diese Perfluoralkyleinheit ausgewählt ist aus der Gruppe bestehend aus  $C_8F_{17}$  bis  $C_{12}F_{25}$ .
6. Gegenstand nach Anspruch 2, wobei R' ausgewählt ist aus der Gruppe bestehend aus Methyl, Ethyl, Vinyl und Propyl.
7. Gegenstand nach Anspruch 3, wobei X ausgewählt ist aus der Gruppe bestehend aus Chlor, Brom, Iod, Methoxy, Ethoxy und Acetoxy.
8. Gegenstand nach Anspruch 2, wobei dieses Perfluoralkylalkylsilan ausgewählt ist aus der Gruppe bestehend aus Perfluoralkylethyltrichlorsilan, Perfluoralkylethyltrimethoxysilan, Perfluoralkylethyltriethoxysilan, Perfluoralkylethyltriethoxy(methyl)silan und Perfluoralkylethyltriethoxy(methyl)silan.
9. Gegenstand nach Anspruch 8, wobei diese Zusammensetzung weiterhin ein fluoriertes Olefin enthält.



# EP 0 719 743 B1

10. Gegenstand nach Anspruch 1, wobei dieses vollständig hydrolysierbare Silan ausgewählt ist aus der Gruppe bestehend aus Silanen der allgemeinen Formel  $\text{SiX}_4$ , worin X ausgewählt ist aus der Gruppe bestehend aus Halogen-, Alkoxy- und Acylresten.
- 5 11. Verfahren zur Herstellung einer nicht benetzbaren Oberfläche auf einem Substrat, umfassend Inkontaktbringen einer Oberfläche mit einer Zusammensetzung, die eine Mischung aus Perfluoralkylalkylsilan und vollständig hydrolysierbarem Silan enthält, wobei dieses Substrat ausgewählt ist aus der Gruppe bestehend aus Glas, Kunststoffen, Metallen, mit einem organischen Polymer beschichteten Substraten und anorganisch beschichteten Substraten, wobei dieser Mischung kein Wasser zugesetzt ist.
- 10 12. Verfahren nach Anspruch 11, wobei dieses Perfluoralkylalkylsilan ausgewählt ist aus Verbindungen mit der allgemeinen Formel  $\text{R}_m\text{R}'_n\text{SiX}_{4-m-n}$ , worin R ein Perfluoralkylalkylrest ist, R' ein Vinyl- oder ein Alkylrest ist,  $m+n$  kleiner als 4 ist und X ein Rest ist, der ausgewählt ist aus der Gruppe bestehend aus Halogen-, Alkoxy- und Acylresten.
- 15 13. Verfahren nach Anspruch 12, wobei die Perfluoralkyleinheit dieses Perfluoralkylalkylrestes ausgewählt ist aus der Gruppe bestehend aus  $\text{CF}_3$  bis  $\text{C}_{30}\text{F}_{61}$ .
14. Verfahren nach Anspruch 13, wobei diese Perfluoralkyleinheit ausgewählt ist aus der Gruppe bestehend aus  $\text{C}_6\text{F}_{13}$  bis  $\text{C}_{18}\text{F}_{37}$ .
- 20 15. Verfahren nach Anspruch 14, wobei diese Perfluoralkyleinheit ausgewählt ist aus der Gruppe bestehend aus  $\text{C}_8\text{F}_{17}$  bis  $\text{C}_{12}\text{F}_{25}$ .
16. Verfahren nach Anspruch 12, wobei R' ausgewählt ist aus der Gruppe bestehend aus Methyl, Ethyl, Vinyl und Propyl.
- 25 17. Verfahren nach Anspruch 12, wobei X ausgewählt ist aus der Gruppe bestehend aus Chlor, Brom, Iod, Methoxy, Ethoxy und Acetoxy.
- 30 18. Verfahren nach Anspruch 11, wobei diese Zusammensetzung weiterhin ein fluoriertes Olefin enthält.
19. Verfahren nach Anspruch 11, wobei das hydrolysierbare Silan ausgewählt ist aus der Gruppe bestehend aus Silanen der allgemeinen Formel  $\text{SiX}_4$ , worin X ausgewählt ist aus der Gruppe bestehend aus Halogen-, Alkoxy- und Acylresten.
- 35 20. Verfahren nach Anspruch 11, wobei die Substratoberfläche zuerst mit einer Schicht aus Siliciumdioxid grundiert wird.

## Revendications

- 40 1. Article comprenant un support dont au moins une partie de la surface est traitée par une composition comprenant un mélange de perfluoralkylalkylsilane et de silane totalement hydrolysable, où le support est choisi dans le groupe formé par le verre, les matières plastiques, les métaux, les supports revêtus de polymères organiques et les supports revêtus de matières inorganiques, où l'on n'ajoute pas d'eau audit mélange.
- 45 2. Article suivant la revendication 1, caractérisé en ce que l'on choisit ledit perfluoralkylalkylsilane parmi des composés de la formule générale  $\text{R}_m\text{R}'_n\text{SiX}_{4-m-n}$ , dans laquelle R représente un radical perfluoralkylalkyle, R' représente un radical vinyle ou un radical alkyle,  $m+n$  est inférieur à 4 et X est choisi dans le groupe formé par les radicaux halogène, alkoxy et acyle.
- 50 3. Article suivant la revendication 2, caractérisé en ce que le groupement perfluoralkyle dudit radical perfluoralkylalkyle est choisi dans le groupe formé par les composés  $\text{CF}_3$  à  $\text{C}_{30}\text{F}_{61}$ .
- 55 4. Article suivant la revendication 3, caractérisé en ce que ledit groupement perfluoralkyle est choisi dans le groupe formé par les composés  $\text{C}_6\text{F}_{13}$  à  $\text{C}_{18}\text{F}_{37}$ .
5. Article suivant la revendication 4, caractérisé en ce que ledit groupement perfluoralkyle est choisi dans le groupe formé par les composés  $\text{C}_8\text{F}_{17}$  à  $\text{C}_{12}\text{F}_{25}$ .

6. Article suivant la revendication 2, caractérisé en ce que R' est choisi dans le groupe formé par les radicaux méthyle, éthyle, vinyle et propyle.
7. Article suivant la revendication 3, caractérisé en ce que X est choisi dans le groupe formé par le chlore, le brome, l'iode, les radicaux méthoxy, éthoxy et acétoxy.
8. Article suivant la revendication 2, caractérisé en ce que le perfluoralkylalkylsilane est choisi dans le groupe formé par les composés qui suivent : Perfluoralkyléthyltrichlorosilane, perfluoralkyléthyltriméthoxysilane, perfluoralkyléthyltriacétoxysilane, perfluoralkyléthylchloro(méthyl)silane et perfluoralkyléthyl-diéthoxy(méthyl)silane.
9. Article suivant la revendication 8, caractérisé en ce que ladite composition comprend en outre une oléfine fluorée.
10. Article suivant la revendication 1, caractérisé en ce que ledit silane complètement hydrolysable est choisi dans le groupe formé par les silanes qui répondent à la formule générale  $\text{SiX}_4$ , dans laquelle X est choisi dans le groupe formé par les atomes d'halogènes, les radicaux alcoxy et acyle.
11. Procédé de production d'une surface non mouillante sur un support, qui comprend la mise en contact d'une surface avec une composition qui comprend un mélange de perfluoralkylalkylsilane et de silane complètement hydrolysable, où ledit support est choisi dans le groupe constitué par le verre, les matières plastiques, les métaux, les supports revêtus de polymères organiques et les supports revêtus de matières inorganiques, où l'on n'ajoute pas d'eau audit mélange.
12. Procédé suivant la revendication 11, caractérisé en ce que ledit perfluoralkylalkylsilane est choisi parmi des composés de la formule générale  $\text{R}_m\text{R}'_n\text{SiX}_{4-m-n}$ , dans laquelle R représente un radical perfluoralkylalkyle, R' représente un radical vinyle ou un radical alkyle,  $m+n$  est inférieur à 4 et X est choisi dans le groupe formé par les radicaux halogène, alcoxy et acyle.
13. Procédé suivant la revendication 12, caractérisé en ce que le groupement perfluoralkyle dudit radical perfluoralkylalkyle est choisi dans le groupe formé par les composés  $\text{CF}_3$  à  $\text{C}_{30}\text{F}_{61}$ .
14. Procédé suivant la revendication 13, caractérisé en ce que ledit groupement perfluoralkyle est choisi dans le groupe formé par les composés  $\text{C}_6\text{F}_{13}$  à  $\text{C}_{18}\text{F}_{37}$ .
15. Procédé suivant la revendication 14, caractérisé en ce que ledit groupement perfluoralkyle est choisi dans le groupe formé par les composés  $\text{C}_8\text{F}_{17}$  à  $\text{C}_{12}\text{F}_{25}$ .
16. Procédé suivant la revendication 12, caractérisé en ce que R' est choisi dans le groupe formé par les radicaux méthyle, éthyle, vinyle et propyle.
17. Procédé suivant la revendication 12, caractérisé en ce que X est choisi dans le groupe formé par le chlore, le brome, l'iode, les radicaux méthoxy, éthoxy et acétoxy.
18. Procédé suivant la revendication 11, caractérisé en ce que ladite composition comprend en outre une oléfine fluorée.
19. Procédé suivant la revendication 11, caractérisé en ce que le silane hydrolysable est choisi dans le groupe formé par les silanes répondant à la formule générale  $\text{SiX}_4$ , dans laquelle X est choisi dans le groupe formé par les atomes d'halogènes, les radicaux alcoxy et acyle.
20. Procédé suivant la revendication 11, caractérisé en ce que la surface du support est d'abord revêtue d'une couche primaire de silice.